

THIS INFORMATION IS FOR THE USE OF CORROCOAT PERSONNEL & DISTRIBUTORS ONLY

| | |
|-------------------------------|--|
| TYPE: | A cold cured 100% solids epoxide, specially modified to give a low roughness amplitude with poor wet out properties. |
| SUGGESTED USE: | The purpose of Fluiglide 'E' is to offer a smooth uninterrupted surface, increasing flow in the boundary layer whilst affording some degree of resistance to abrasion. |
| LIMITATIONS: | Fluiglide 'E' does not give the same performance as Fluiglide but is able to withstand more arduous service conditions. The upper temperature limit is 212°F (100°C). |
| HEALTH & SAFETY: | Safety precautions should be observed when handling this material. Skin contact should be avoided and eye protection, gloves and protective clothing worn. Sensitization of the skin may occur if these precautions are not observed, otherwise this material is safe in use provided normal precautions for epoxy resins are observed. |
| SURFACE PREPARATION: | The surface should be prepared by grit blasting to Swedish Standard SA3 with an ideal profile of around 3 mils (75 microns). |
| APPLICATION EQUIPMENT: | Spray and brush. |
| APPLICATION: | Fluiglide 'E' may be applied direct to the substrate except in the case of concrete. The material should be applied in at least two coats of between 10 to 12 mils (250 to 350 microns) with a minimum d.f.t. of 20mils (500 microns). Where build up of damaged components is required this should be carried out first using Corrocoat EA and EB. Fluiglide 'E' should then be applied as a top coat to these products. Care should be taken to observe overcoating times and application during periods of high humidity (in excess of 85% RH) should be avoided. Where this material is used in a potable water environment, allow 7 days at and above 64.4°F (18°C) prior to service. Fluiglide 'E' is approved for use for factory applied products. |
| MIXING RATIO: | 2:1 Base to Activator by weight. |
| MIXING: | Weigh out 2 parts of Fluiglide 'E' base (white color) to 1 part of Fluiglide 'E' activator (straw colored liquid) by weight. Thoroughly mix the two components with a suitable implement, preferably by power stirring until the material is an even color containing no streaks of unmixed material. |
| POT LIFE: | At 68°F (20°C) Fluiglide 'E' is usable for approximately 30 minutes with a gel time of 45 minutes. As temperature increases pot life reduces but cold temperatures will extend pot life. |
| PACKAGING: | 5 gallon (18.9 liter) composite kits |

FLUIGLIDE

FLUIGLIDE "E"

Page 2 of 2

| | |
|---------------------------|--|
| STORAGE LIFE: | 18 months unopened at temperatures below 86°F (30°C) |
| COLOR AVAILABILITY: | White. Dye should not be used with this product. |
| RECOMMENDED DFT: | Minimum of 20 mils (500 microns) in two coats. |
| PRACTICAL SPREADING RATE: | 24.44 ft ² /gal at 20 mils dft (0.6 litres/m ² at 500 microns dft). |
| | Note: This information is given in good faith but may increase dependent upon environment conditions, the geometry and nature of work undertaken and the skill and care of application. Corrocoat accept no responsibility for any deviation from these values. |
| VOLUME SOLIDS: | 100% solvent free. |
| SPECIFIC GRAVITY: | .0412 lbs/in ³ (1.14 gms/cc) |
| FLASH POINT: | 203°F (95°C) |
| TEMPERATURE LIMITS: | Upper: 212°F (100°C) (dependent upon environment) Lower: No known limit. |
| ACTIVATOR TYPE: | Aliphatic Polyamide. |
| OVERCOATING TIME: | At 68°F (20°C) minimum 4 hours, maximum 30 hours. |
| CURE TIME: | Minimum service time 36 hours Potable water 7 days at 64.4°F (18°C). |
| CLEANING SOLVENT: | Acetone, methyl ethyl ketone, methyl iso butyl ketone, or toluene before gel. |
| NOTE: | DESIGN PARAMETERS SHOULD BE TAKEN INTO ACCOUNT WHEN USING THIS MATERIAL TO INCREASE PUMP EFFICIENCIES. MAXIMUM BENEFIT CAN ONLY BE OBTAINED BY KEEPING COATING THICKNESS TO MINIMUM RECOMMENDATION. SOME ITEMS WITH NARROW PASSAGEWAYS WILL NOT BENEFIT FROM THE APPLICATION OF THIS MATERIAL. |

WHERE DOUBT EXISTS - SEEK ADVICE

Reviewed 12/2007
Reviewed 06/2011
Reviewed 07/2011
Reviewed 06/2012
U.S. Revision 06/2014