

TYPE:	A VISCOUS, SOLVENT FREE, TWO OR THREE PACK, AMINE CURED EPOXY, CONTAINING BOTH STAINLESS STEEL FLAKES, GLASS FLAKES AND SILICON CARBIDE.			
SUGGESTED USE:	Areas requiring abrasion (and chemical) resistance. This material has been used in cyclones, chemical process vessels, sugar beet pulping drums etc. It is also useful for building up damaged areas of pump impellers and casings where impact or abrasion are prevalent.			
LIMITATIONS:	Dependent upon environment , Immersed conditions: 135°C. Non-immersed conditions: 338°F (170°C).			
HEALTH & SAFETY:	Before handling or using this product the material safety data sheet should be read and all precautions observed.			
SURFACE PREPARATION:	To obtain optimum adhesion the substrate should be grit blasted to Swedish Standard SA 2.5 with 3 mils (75 micron) profile. If grit blasting is not possible, smooth surfaces should be roughened and scored by grinding to give the coating a key. Under these conditions there will be some reduction in adhesion properties. A release agent should be used for any surface to which the coating should not adhere.			
APPLICATION EQUIPMENT:	Trowel, putty knife, stiff brush or other suitable implement.			
APPLICATION:	This material is intended for application at thicknesses between 1.5 to 4mm. It not normally applied at less than 1mm thickness but can be built up to any desired thickness provided care is taken to avoid pronounced exothermic temperature rises. Material should only be applied when the surface temperature is between 46.4°F and 104°F (8°C and 40°C). The surface temperature should be 41°F (5°C) above dew point and humidity below an RH value of 90%. It is advisable to check for 'amine bloom' . Where this is suspected by visual appearance or where the environmental and ambient temperatures are outside the above limits. A suitable 'bloom' test kit may be used			
MIXING RATIO:	2.5 Parts base to 1 part activator by weight.			
MIXING INSTRUCTIONS:	Remove lids from both components A-Activator and B-Base and scoop out all of component A putting into component B. Mix thoroughly, ensuring that no unmixed material remains. Remove all mixed material from base tin and re-mix on a clean flat surface or shallow receptacle. After mixing, the material remains usable for a limited period dependent upon temperature, after which time application becomes difficult. Mix only sufficient material that can be applied with the limited pot life.			
POT LIFE:	Temp °F (°C)	68 (20)	86 (30)	104 (40)
	Usable time (minutes)	50	20	15
	To increase pot life at high ambient temperatures refrigerate material prior to use to a minimum temperature of 50°F (10°C). Gel times will vary depending on temperature and quantity.			
THINNERS:	DO NOT THIN. Any addition of solvent will be detrimental to performance.			
PACKAGING:	5 gallon (18.9 liter) composites.			

STORAGE LIFE:	1 year minimum in unopened tins stored below 95°F (35°C).
COLOR AVAILABILITY:	Speckled grey.
RECOMMENDED DFT:	As a general lining 2mm, any desired thickness build up.
THEORETICAL SPREADING RATE:	40.74ft ² /gal (1m ² /litre) at 1mm thickness.
VOLUME SOLIDS:	100%
PRACTICAL SPREADING RATE:	34.63ft ² /gal (0.85m ² /litre) at 1mm thickness. Note: This information is given in good faith but may increase dependent upon environment conditions, the geometry and nature of work undertaken, and the skill and care of application. Corrocoat accept no responsibility for any deviation from these values.
SPECIFIC GRAVITY:	.0495lbs/in ³ (1.37gcm ³) mixed
FLASH POINT:	Greater than 230°F (110°C)
ACTIVATOR TYPE:	Formulated Amine
MIXING RATIO:	2.5:1 Base to hardener W/W
ADHESIVE STRENGTH:	Greater than 10 MPa
HARDNESS:	45 to 50 Barcol
CURE TIME:	24 hours at 68°F (20°C). Although the cold cured properties of this material are excellent they may be improved further by post curing. This can be achieved by applying heat at 140 to 212°F (60 to 100°C) for periods up to 24 hours at which time maximum possible cure will have been attained. Post cure for shorter periods will also improve the characteristics of this material.
OVERCOATING TIME:	Maximum over-coating time is 12 hours at 68°F (20°C). The minimum over-coating time is 1 hour at 68°F (20°C) (2mm coating thickness). At different temperatures these times will vary, being shorter at higher temperatures and longer at lower temperatures. Amine bloom may cause intercoat adhesion failure. Refer to 'Application' above.
CLEANING SOLVENT:	Acetone, methyl ethyl ketone, xylene.
CHEMICAL RESISTANCE:	Excellent

All values are approximate. Information regarding application of the product is available in the Corrocoat manual. Should further information be required, please consult Corrocoat Technical Services.

Reviewed 02/2014 (No change)
U.S. Revision 06/2014