

TYPE:	A TWO-PACK PEROXIDE CATALYZED VINYL ESTER GLASS FLAKE PRIMER.
SUGGESTED USE:	A holding primer on metal substrates for Polyglass VE/VEF where service temperatures are in excess of 176°F (80°C). Also be used for adhesion promotion between existing Polyglass VE and a repair or new top coat. Use PPA wherever service duty allows.
LIMITATIONS:	PPV must not be used where damp conditions exist and pH is above 9. Strong sunlight will cause rapid cure and substantially reduce overcoating time as will high ambient temperature.
HEALTH & SAFETY:	Before handling or using this product the material safety data sheet should be read and all precautions observed.
SURFACE PREPARATION:	Metals: Grit blast to SSPC-SP10 (ISO standard 8501-1 Sa 2½. SSPC-SP 10). (For full details refer to Corrocoat Surface Preparation SP1.) Concrete: Consult Tech Services. Generally not recommended except as a sealer , test patches should be applied first to confirm bond and cure.
APPLICATION EQUIPMENT:	Airless pump 30:1 minimum ratio is recommended with 3/8" (10mm) diameter nylon lined hose and 6mm whip end. Seals should preferably be of leather and PTFE and all fluid filters must be removed. Tip size 18 to 30thou with reverse clean and a 45° fan pattern. The size of tip and fan pattern will vary dependent upon the nature of the work. Use pressure to suit hose lengths and working conditions. (circa 200bar). Brush and roller may also be used.
APPLICATION:	Apply as a single coat at a wet film thickness of between 2 and 5 mils (50 and 120 microns). Over thickness will increase tack free time. For this product to cure it is essential that good ventilation is achieved. For application to concrete consult Corrocoat TSD, PPV Primer should not be used where there is a high moisture content or risk of contaminants above pH 9 during cure or temperature is below 37°F (3°C).
RECOMMENDED DFT:	DFT is not specified. Wet film thicknesses should be checked and be within the range 2 and 6 mils (50 to 150 microns) maximum during application.
MIXING RATIO/MIXING:	98:2 base to hardener weight/weight. For temperatures below 59°F (15°C) add catalyst to base product and mix vigorously with a mechanical stirrer for not less than 2 minutes. For temperatures above 59°F (15°C), first add retarder and stir by mechanical agitator for 2 minutes then Allow a minimum of 3 minutes before the addition of catalyst which should again be stirred in vigorously with a mechanical stirrer for not less than 2 minutes. Adding Retarder after the Catalyst will ruin the product . Procedures for spray application are similar to those for Polyglass and the Polyglass application data sheet should be read before the mixing or application of this product.
PACKAGING:	5 Gallon (18.9 liter) drum with catalyst.
STORAGE LIFE:	Base and Hardener - 6 months in unopened drums which should be stored below 75°F (24°C), away from heat sources and out of direct sunlight.

POLYGLASS

PPV**Page 2 of 2**

COLOR AVAILABILITY:	Clear, slightly amber.
THEORETICAL SPREADING RATE:	814-407 SF/Gal at 2-4 mils (20-10 M ² /Liter at 50-100 microns) WFT.
VOLUME SOLIDS:	This material contains volatile liquid convertible to solids. Volume solids obtained will vary dependent upon polymerisation conditions. Nominally 91% of the contents are converted to solid.
PRACTICAL SPREADING RATE:	Steel: Approximately 652-326 SF/Gal at 2-4 mils (16-8 M ² /Litre at 50-100 microns) WFT. Concrete: Approximately 489-244 SF/Gal at 2-4 mils (12-6 M ² /Liter at 50-100 microns) WFT. Note: This information is given in good faith but rate may vary significantly dependent upon environmental conditions, the geometry and nature of work undertaken and the skill and care of application. Corrocoat accepts no responsibility for any deviation from these values.
SPECIFIC GRAVITY:	.04 Lbs Cu/Inch (1.06 gms/cc)mixed. FLASH POINT: 82°F (28°C).
CATALYST TYPE:	Methyl Ethyl Ketone Peroxide, type P2.
MIXING RATIO:	98:2 base to activator by weight.
DRYING TIME:	Tack free with good ventilation - 90 minutes, 50°F at 2-4 mils (10°C at 50-100 microns) WFT. Tack free 50 minutes, 68°F at 2-4 mils (20°C at 50-100 microns) WFT.
OVERCOATING:	It is important to observe maximum overcoating times and note these will vary with climatic conditions. Dependent upon temperature and ventilation level, minimum at 68°F (20°C) with good ventilation 1.5 hours. Maximum at 68°F (20°C), 3 days. Strong ultra-violet / sunlight will substantially reduce overcoating time. Once the maximum overcoating time has been reached, adhesion values attained by any subsequent coat will reduce drastically . Any further application of coating at this juncture should be treated as a repair, with the surface flash blasted to provide a physical key. Styrene cannot be used to reactivate the surface of this product and may impair adhesion . Care should be taken to avoid contamination of applied PPV Primer before application of subsequent materials.
CLEANING SOLVENT:	Methyl Ethyl Ketone before gelation.
POT LIFE:	Variable dependent upon temperature, but approximately 2 hours at 50°F (10°C), 1 hour at 68°F (20°C).
THINNERS:	This product should not be diluted or thinned. The use of thinners is detrimental to performance except where advised for use with concrete.

All values are approximate. Information regarding application of the product is available in the Corrocoat manual. Should further information be required, please consult Corrocoat Technical Services.

Corrocoat USA, Inc., 6525 Greenland Road, Jacksonville, FL 32258 | 904-268-4559 | www.corrocoatusa.com

This information is offered in good faith but without guarantee or liability