

TYPE:	<b>A TWO PACK COLD CURED VINYL ESTER/ACRYLIC CO-POLYMER ENHANCED WITH FLAKED GLASS, SPECIFICALLY FORMULATED TO BE APPLIED USING A CENTRIFUGAL PIPE ROLLING RIG.</b>
SUGGESTED USE:	Immersed environments where superior resistance to chemical attack is required, VE is suitable for most chemical environments within the pH range of 0 to 13 and is unaffected at temperatures up to 194°F (90°C) by demineralized water. It also has excellent resistance to most solvents. May be used in aggressive atmospheric or spillage conditions.
LIMITATIONS:	Affected by some highly polar solvents and solutions exhibiting high pH at temperatures above 122°F (50°C).
HEALTH & SAFETY:	Before handling or using this product the material safety data sheet should be read and all precautions observed.
SURFACE PREPARATION:	Metals: Grit blast to SSPC-SP10 (SIS 05 5900 SA 2.5 standard). For full details refer to Corrocoat Surface Specification SP1. Concrete: Grit blast to remove surface laitance. See Corrocoat Surface Specification SP5.
APPLICATION EQUIPMENT:	Specialized pipe rolling equipment.
APPLICATION:	Dependent on intended use and prevailing site conditions, but Polyglass VE Pipe Grade is normally applied in wet films between 40 and 80 mil (1000 and 2000 microns). For further details see Polyglass Application Data Sheet.
MIXING RATIO/MIXING:	98:2 base to hardener. For inhibitor use and mixing instructions refer to Polyglass Application Data Sheet.
POT LIFE:	Variable to suit site conditions, refer to Polyglass Application Data Sheet, typically for Pipe Grade 25-30 minutes at 68°F (20°C).
THINNERS:	The performance of Polyglass VE Pipe Grade can be adversely affected by the addition of solvent thinners and their use is prohibited. Thinning can be achieved by the addition of not more than 5:100 styrene monomer to Polyglass Pipe Grade by volume i.e. maximum .33 Gal (1.25 liters) styrene per 7 Gal (26.5 liters) Polyglass Pipe Grade. It should be noted that dilution with styrene may affect chemical resistance.
PACKAGING:	5 Gallon (18.9 liter) composites.
STORAGE LIFE:	6 months stored at temperatures below 68°F (20°C) and away from heat sources and direct sunlight. Frequent temperature cycling will shorten storage life. See other information for extension of shelf life.

COLOR AVAILABILITY:	Unpigmented (Translucent Brown) and Off White only. Other colors are not available and it should be noted that the addition of dyes will adversely affect chemical resistance.
RECOMMENDED DFT:	Between 30 and 120 mils (750 and 3000 microns) dependent upon environment.
THEORETICAL SPREADING RATE:	54 SF/Gal at 30 mils (1.33m <sup>2</sup> /liter at 750 microns).
VOLUME SOLIDS:	This material contains volatile liquid convertible to solids. Volume solids obtained will vary dependent upon polymerization conditions. Nominally 99.05% of the contents are convertible to solid.
PRACTICAL SPREADING RATE:	43 SF/Gal at 30 mils (1.06m <sup>2</sup> /liter at 750 microns).  <b>Note:</b> This information is given in good faith but may increase dependent upon environment conditions, the geometry and nature of work undertaken and the skill and care of application. Corrocoat accept no responsibility for any deviation from these values.
SPECIFIC GRAVITY:	VE Pipe Grade base: 1.18 gms/cc. Hardener: 1.07 gms/cc.
FLASH POINT:	82°F (28°C).
CATALYST TYPE:	Methyl Ethyl Ketone Peroxide, type P2-45.
MIXING RATIO:	98:2 base to hardener, refer to Application Data Sheet for inhibitor levels.
HARDNESS:	45 Barcol.
TENSILE STRENGTH:	3874 psi (26.7 N/mm <sup>2</sup> )
ELONGATION AT BREAK:	0.4%.
THERMAL COEFFICIENT OF LINEAR EXPANSION:	19.7 x 10 <sup>-6</sup> /°C.
DIELECTRIC STRENGTH:	18 - 25 x 10 <sup>3</sup> V/mm
THERMAL CONDUCTIVITY:	0.398 W/m°K.
TEMPERATURE LIMITS:	230°F (110°C) immersed. 347°F (175°C) non-immersed. No known lower limit.
OVERCOATING:	May take place as soon as the previous coat has gelled and whilst still tacky. Maximum overcoating time is 72 hours. For times in excess of 72 hours and for overcoating on concrete substrates, refer to Corrocoat for special instructions.
CURING TIME:	With standard inhibitor level, tack free 6 hours, full cure 3-4 days at 68°F (20°C), but may be immersed in many environments after 24 hours.
CLEANING FLUID:	Methyl Ethyl Ketone, Methyl Iso Butyl Ketone - before gel.