

TYPE:	<b>AN ABRASION RESISTANT GLASS FLAKE VINYL ESTER CO- POLYMER.</b> This product is similar to VEF but has abrasion resistant fillers incorporated to improve abrasion and erosion resistance.
SUGGESTED USE:	Immersion environments where superior resistance to chemical attack and erosion resistance are required. VEF WR is suitable for chemical environments within the full pH range, it has excellent resistance to a wide range of chemicals and good resistance to many solvents.
HEALTH & SAFETY:	Before handling or using this product the material safety data sheet should be read and all precautions observed.
CHEMICAL RESISTANCE:	<b>Refer to the chemical resistance list for VE.</b> Note: Affected by some highly polar solvents and some solutions above 122°F (50°C) having a high pH.
SURFACE PREPARATION:	<b>Metals:</b> Grit blast to ISO standard 8501-1 Sa 2½. SSPC-SP 10. (For full details refer to Corrocoat Surface Preparation SP1.) <b>Concrete:</b> refer to Corrocoat SP5.
APPLICATION EQUIPMENT:	Airless pump of 45:1 ratio or greater. Fit leather <b>and</b> PTFE seal combination and remove all fluid filters. 10mm diameter (3/8") nylon lined hose with 6mm whip end, large bore gun with reverse clean spray tip. Typical tip size is 28 thou to 48 thou with a 45° to 60° fan. Size of tip and fan angle will vary dependent upon the nature of the work. Note: Tip wear will be high. Pressure to suit hose lengths and working conditions. 2900 psi (circa 200bar). <b>Brush application:</b> may be brush applied onto small areas with care.
APPLICATION:	Dependent on intended use and site conditions, Polyglass VEF WR is normally applied direct to the surface wet on wet at films between 20 and 48 mils (500 and 1200 microns). <b>Single coat applications are acceptable.</b> Where logistics demand, primer PPA may be used or PPN for temperatures over 185° F (85°C). For further details see Polyglass Application Data Sheet.
RECOMMENDED DFT:	Between 19 and 118 mils (500 and 3000 microns) dependent upon duty and environment. This material is a barrier coating and the thickness needed is dependent upon service conditions.
MIXING RATIO/MIXING:	98:2 base to hardener. For inhibitor use and mixing instructions refer to Polyglass Application Data Sheet. <b>Adding inhibitor after the catalyst will ruin the product.</b>
POT LIFE:	Circa 50 minutes at 68°F ( 20 °C) but may be varied by use of inhibitor or special manufacture for low application temperatures, refer to Polyglass Application Data Sheet.
THINNERS:	Polyglass VEF WR is <b>adverely</b> affected by the addition of <b>solvents</b> and their use is prohibited. Thinning can be achieved by the addition of no more than 1 liter of styrene monomer per 5.3 gallons (20 liters) of Polyglass. It should be noted that dilution with styrene may <b>affect hold up</b> and chemical resistance.
PACKAGING:	5 gallon Kits (18.9 liter) composites.
STORAGE LIFE:	Base and catalyst (Hardener) 6 months, stored at temperatures below 68° (20°C), away from heat sources and out of direct sunlight. Frequent temperature cycling will shorten storage life. See 'other information' in the Corrocoat 'Tech Manual' for extension of shelf life.

# POLYGLASS

## POLYGLASS VEF WR

### Page 2 of 2

COLOR AVAILABILITY:	Standard. Off White. Other colors may be available on request.
THEORETICAL SPREADING RATE:	54 SF/Gallon at 29 mils (1.33m <sup>2</sup> /liter at 750 microns).
VOLUME SOLIDS:	This material contains volatile liquid convertible to solids. Volume solids obtained will vary dependent upon polymerization conditions. Nominally 99% of the product is convertible to solid.
PRACTICAL SPREADING RATE:	43 SF/Gallon at 30 mils (1.06m <sup>2</sup> /liter at 750 microns). <b>Note:</b> This information is given in good faith but <b>rate may vary significantly</b> dependent upon environmental conditions, the geometry, nature of work undertaken and the skill and care of application. Corrocoat accepts no responsibility for any deviation from this value.
SPECIFIC GRAVITY:	Polyglass base: .045 Lbs/Cubic inch. (1.25gms/cc). Hardener: . 0 3 8 L b s / C u b i c i n c h ( 1.07) gms/cc.
CATALYST TYPE:	Methyl Ethyl Ketone Peroxide, type P2-45.
MIXING RATIO:	98:2 base to hardener, refer to Application Data Sheet for inhibitor levels.
FLASH POINT:	82.4°F (28°C).
HARDNESS:	Greater than 40 Barcol after full cure.
TEMPERATURE LIMITS:	230°F (110°C) immersed. 329°F (165°C) non-immersed. No known lower limit.
ABRASION RESISTANCE: OVERCOATING:	122 mg loss/1000 cycles/1000 gm load. <b>It is important to observe maximum overcoating times and note these will vary substantially with climatic conditions.</b> Minimum, as soon as gel has occurred and whilst still tacky. Maximum, at 68°F (20°C) 48 hours. Strong ultra-violet/ <b>sunlight will substantially reduce overcoating</b> time. Once maximum overcoating time has been reached, adhesion values attained by any subsequent coat will reduce dramatically. Should this occur overcoating should be treated as a repair, with the coating flash blasted to provide a physical key. Styrene <b>cannot be used</b> to reactivate the surface of this product and may impair adhesion. Take care to avoid contamination before application of subsequent coats. Ensure ventilation during cure.
CURING TIME:	With standard inhibitor level, tack free circa 6 hours, full cure 3-4 days at 68°F (20°C), but may be immersed in many environments after 24 hours. Best chemical and abrasion resistance is obtained with short post cures.
CLEANING FLUID:	Methyl Ethyl Ketone, Methyl Iso Butyl Ketone - before gel.

**All values are approximate. Physical data is based on the product being in good condition before polymerisation, correctly catalysed and full cure being Attained. Information regarding application of the product is available in the Corrocoat manual. Should further information be required, please consult Corrocoat Technical Services.**

**Reviewed 08/2011  
US Revision 8/2016**